

**Product Overview:**

PolyMaster 1.5 is a fast reacting two-component polyurethane injection resin formulated to waterproof and fortify water-bearing structures. PolyMaster 1.5 excels at swiftly halting water ingress.

Its exceptional penetration into cracks, voids, and porous substrates, coupled with its hydrophobic and viscous nature, allows the resin to displace and expel incoming water. At the interface between the resin and water, PolyMaster 1.5 forms stable and durable foam seals. Applications include but are not limited to: stabilisation water bearing ground, halting water inrush in tunnels and dams, slab jacking.

Training is advised for the applicator should the application of PolyMaster 1.5 be slabjacking.

**Technical Data:**

All values listed are approximations.

**Component A:**

Colour:	Yellow tint
Density at 23°C (g/cm <sup>3</sup> )	1.10
Dynamic viscosity at 23°C (mPas)	10000

**Component B:**

Colour:	Brown
Density at 23°C (g/cm <sup>3</sup> )	1.23
Dynamic viscosity at 23°C (mPas)	2200

**A + B**

Mixing ratio by volume (A : B)	1 : 1
Reaction temperature	Exothermic
Viscosity at 23°C (mPas)	140
Cream Time (sec)	30
Gel Time (sec)	80
Track Free Time (sec)	100
Free Density (kg/m <sup>3</sup> )	68
Expansion factor	14 - 16

Although the information and specifications provided in this document are, to the best of our knowledge, accurate and truthful, Deutsch Master recommends that users conduct a trial to confirm the suitability of the product for the intended application. Please note that regional climatic conditions may result in variations in the product's performance. No warranty, express or implied, is provided or implied in connection with any recommendations or suggestions made by Deutsch Master, its representatives, agents, or distributors. The information contained in this technical data sheet is effective from the date shown and supersedes all previous data. Customers should check with their local Deutsch Master office to ensure they are referencing the current version.

**Storage:**

PolyMaster 1.5 has a minimum shelf life of 8 months, in dry conditions as temperatures between 15-25°C. Product should be kept out of direct sunlight. Should you wish to use the product after 8 months, we recommend a sample be sent to Deutsch Master for quality testing.

**Disposal:**

General waste can be used for small quantities of reacted product. Singular components should be disposed of in accordance with local laws.

Although the information and specifications provided in this document are, to the best of our knowledge, accurate and truthful, Deutsch Master recommends that users conduct a trial to confirm the suitability of the product for the intended application. Please note that regional climatic conditions may result in variations in the product's performance. No warranty, express or implied, is provided or implied in connection with any recommendations or suggestions made by Deutsch Master, its representatives, agents, or distributors. The information contained in this technical data sheet is effective from the date shown and supersedes all previous data. Customers should check with their local Deutsch Master office to ensure they are referencing the current version.